RG104 E-1 Box 121

WEEKLY REPORT OF GOLD DEPOSITS MELTED AT UNITED STATES MINT.

1880

Date.	Assay No.	Name of Depositor.	Weight before Melting. Oz.	Dec.	Weight after Melting. Oz.	Dec.	Loss. Oz.	Dec.	Loss per ct.		Gain. Oz.	Dec.	Description of Bullion.	Notes of Melter and Refiner.
March 15th	491	Bernard Levy	35	15	35	09		06		17			Bar	The deposits are from the following sources:
	2	G. C. Thompson	18	31	12	97	5	34	15	60			Jewelry Witch Cases	
	3	do	44	10	43	44		66	1	50			Ring	N. Carolina (1) 3
	4	Hastings & Co.	134	34	134	34							U.S. Coin	Georgia 2
	5	do	24	99	23	97	1	02	4	08			Buttons, Leg. &c.	Alabama (1) 1
	6	Peter Mulryan	40	65	40	64		01		02			For. Coin	Philad^a (1) 1
	7	Richd Helms	26	87	26	87							U.S. Coin	Wyoming 1
	8	Wm H. Lee	50	79	50	75		04		08			Bar	Africa 1
	9	do	10	51	10	51							Button	Finer bullion (3) 13
	10	Phillips & Jacobs	53	74	53	74							U.S. Coin	Baser " — 3
	1	Morgan, Hastings & Co.	80	60	80	60							U.S. Coin	Jewelry, &c. 7
	2	John Stuart	4	43	4	42		01		25			Button	Very base bullion 3
	3	Johnson & Lund	9	48	9	35		13	1	44			Dif & Filings	Dent plate 2
16th	4	G. C. Thompson	25	02	20	46	4	56	18	24			Jewelry, Witch Cases, &c.	For coin 10
	5	do	59	95	58	00	1	95	3	25			Grs, Africa	Total 47
	6	Lloyd, Supplee & Walton	14	08	13	44		64	4	57			Grs. & Amal, Gen.	
	7	J. B. Lippincott & Co.	7	03	7	02		01		14			Buttons, Ala.	The loss in melting the
17th	8	G. C. Thompson	11	54	10	67		87	7	35			Button	finer bullion, 0.10 %, is
	9	H. H. Shearer & Co.	40	00	39	74		26		65			Button	rather too low; — the baser
	90	G. C. Thompson	43	60	39	53	4	07	9	25			Jewelry, Witch Cases &c.	bullion, 3.94 %, is about
	1	Drexel & Co.	15	32	15	32							For. Coin	a fair medium; — jewelry
	2	E. Kretzmer	8	45	6	22	2	23	27	87			Button, Base	&c. 17.05 % is quite full
	3	Alex. Hay	159	16	159	16							Bar, U.S. Mint, Phil^a	but not too full; — very base
	4	Wm H. Lee	22	63	22	60		03		13			Bar	bullion, 28.31 %, is a fair
18th	5	R. S. Lindsay	7	74	7	55		19	2	37			Bar & Amal, N. C.	average or within it.
	6	G. C. Thompson	27	58	21	09	6	49	23	18			Jewelry Witch Cases	The loss on coin 0.004 %,
	7	do	14	12	8	87	5	25	37	50			Ring, Base	is too low for 10 deposits,
	8	Richd Helms	26	86	26	86							U.S. Coin	which could not be worked
	9	G. C. Thompson	9	75	9	00		75	7	50			Jewelry, Witch Cases	without a greater loss. The loss
19th	500	do	32	49	25	04	7	45	23	28			Jewelry, Witch Cases, &c.	on dental plate, 1.77 % is
	1	S. C. Jump	9	88	9	87		01		10			Bar	a fair amount.
	2	Phillips & Jacobs	53	74	53	73		01		02			U.S. Coin	The loss in melting the night
	3	R. H. Seal	52	75	51	64	1	11	2	09			Filings & Dif.	deposits from N. Carolina are
	4	J. C. Lee	123	52	123	42		10		08			Bar	very diff. No 495, losing 2.37 %
	5	do	18	16	18	19					03		Bar	is fair, but the excess in No
20th	6	Simons, Bro. & Co.	87	60	87	58		02		02			Bars	511 of 12.60 %, is due largely
	7	G. C. Thompson	13	53	13	53							Bars, Gen.	to the very small deposits of
	8	do	9	57	9	57							Bar	2 38/100 oz. The loss on the
	9	do	27	13	21	85	5	38	19	56			Ring, Base	Georgia lots 5.14 %, is fair
	10	do	15	15	14	39		86	5	73			Amal, Gen.	as well as that on the Wyoming
	1	do	2	38	2	08		30	15 3	11			Amal, N. C.	5.76 %. The loss on African
	2	R. Muhr's Sons	17	09	17	09							Bars	grains, 3¼ %, is about the
	3	Drexel & Co.	17	05	16	07		98	5	76			Amal, Wyoming	usual average
	4	G. C. Thompson	29	42	29	42							For. Coin	Jas C Booth
	5	do Remelt 14.73	18	49	14	48	4	01	22	28			Jewelry Witch Cases	
	6	Hastings & Co.	134	33	134	33							U.S. Coin	
	7	A. Loudon Snowden, Supt.	204	01	203	98		03		01			Bars, U.S. Mint, N.C.	
			1890	08	1838	37	51	74	4	39	03			

For week ending March 20th, 1880.

Approximate value, $28,494.73

J. Dobby Danglieu

Register.

To the Director of the Mint.

RG104 E-1 Box 121

Report of Gold Deposits
melted for week ending
March 20th 1880

NARA RG104, Entry 1, Box 121

[Abstract:] Report of Gold Deposits melted for week ending March 20, 1880

Weekly Report of Gold Deposits Melted at United States Mint.

[Please see original images for data table.]